

Australian™

Sustaining our future

Bright White Office Paper

Australian Office Paper is proudly made in Victoria at Australian Paper's Maryvale Mill.

The Maryvale Mill is the largest private sector employer in the Latrobe Valley with over 900 direct employees and many more supported indirectly through the Mill's activities.

The Maryvale Mill has reduced water used per tonne of paper produced by 66% over the past 20 years. As a further water saving initiative, Australian Paper will be supporting the new Gippsland Water Factory (GWF). By collecting and recycling eight million litres of wastewater a day and selling it to Australian Paper for use at the Maryvale Mill, about three billion litres (1200 Olympic-size swimming pools) of fresh water will be saved each year.

Following a major \$350 million pulp mill investment project in 2009, the Maryvale Mill converted its main facility to ECF Lite pulping technology.

Australian Office Paper is Australian Forestry Standard (AS 4707) Certified which means that all fibre used in the manufacture of this product is drawn from sustainably managed forests and controlled sources.



Australian Forestry Standard (AS 4707 & AS 4708) Facts & Figures

- The Australian Forest Certification Scheme (AFCS) Australian Forestry Standard AS 4708 has been used to certify over 10.2 million hectares of native forests and plantations across Australia.
- The AFCS is the leading authoritative voice for forest and wood products certification in Australia.
- Guaranteed minimum mix of 70% certified raw source or recycled material.
- Guaranteed independently audited and verifiable supply chain from forest to end user.
- Guaranteed Australian Standard that provides consistency nationally and internationally.

Australian Office Paper

500
sheet ream

80
gsm weight

A4 & A3
sheet size

150
whiteness

ACID FREE

AUSTRALIAN MADE





Bright White Office Paper

Mill

Maryvale Mill, Victoria, Australia.

Certification

The pulp and paper mill has the following certifications:

- Quality System AS/NZS ISO 9001:2008
- Environmental System AS/NZS ISO 14001:2004
- OH&S AS/NZS 4801:2001
- Australian Forestry Standard (AS 4707) Chain of Custody.

Materials

The major components of Australian Office Paper are Bleached Kraft short and long fibre, filler (calcium carbonate) and starch.

Product Technical Info

The tables below display typical values.

Test climate: Rapid Conditioned @ 50% RH, 23°C.

Physical Properties	Unit	Typical Values	Method based on
Nominal Grammage	g/m ²	80	AS 1301.405s
Moisture	%	4.5	AS 1301.457s
Thickness (Bulking)	µm	102	AS 1301.426s
Roughness (Bendtsen)	ml/min	145	AS 1301.439s
Porosity (Bendtsen)	ml/min	1550	AS 1301.440s
Cobb 1min (multisheet)	g/m ²	26	AS 1301.411s
Wax Pick	number	17	Tappi 459
Visual Properties			
Opacity	%	90.8	AS 1301.454s
CIE Whiteness	-	150	ISO 11475
Fluorescence (Δ D65/10° Brightness)	%	22.2	AS 1301.462s
Dirt Frequency	ppm	1.6	Tappi 563

AUSTRALIAN OFFICE PAPER FEATURES

- Available in A4 & A3 – 80gsm
- Meets the requirements of the International Standard for Permanent Papers (ISO9706)
- Both lignin and acid free
- 100% guaranteed for all printers, faxes & copiers*
- Australian Office Paper is Australian Forestry Standard (AS4707) Certified.

AUSTRALIAN PAPER'S MARYVALE MILL

Australia's largest integrated paper-making complex, Maryvale Mill can produce more than 500,000 tonnes of paper every year. Maryvale is also an industry leader in environmental practice – recycling large amounts of water, using waste products as energy sources, and continuing to reduce both carbon emissions and raw water usage.



*Refer to pack for guarantee details.



AUST4107



1800 882 935
www.leadingbrands.com.au